

BB

1/9/1
DIALOG(R) File 347:JAPIO
(c) 2000 JPO & JAPIO. All rts. reserv.

02262604
PRODUCTION OF RESIN BINDER FOR WATER-BASED FLEXOGRAPHIC INK

PUB. NO.: *62*-179504 [JP. 62179504 A]
PUBLISHED: August 06, 1987 (19870806)
INVENTOR(s): SHIMIZU KATSUHISA
YAMADA KOJI
OKUMURA AKIRA
APPLICANT(s): ARAKAWA CHEM IND CO LTD [350104] (A Japanese Company or Corporation), JP (Japan)
APPL. NO.: 61-021031 [JP 8621031]
FILED: January 31, 1986 (19860131)
INTL CLASS: [4] C08F-002/26; C09D-011/10
JAPIO CLASS: 14.2 (ORGANIC CHEMISTRY -- High Polymer Molecular Compounds);
29.4 (PRECISION INSTRUMENTS -- Business Machines)
JOURNAL: Section: C, Section No. 471, Vol. 12, No. 28, Pg. 121,
January 27, 1988 (19880127)

ABSTRACT

PURPOSE: To produce the titled binder excellent in dryability, film gloss, pigment dispersion etc., by emulsion-polymerizing an ethylenically unsaturated monomer in the presence of a specified protective colloid.

CONSTITUTION: A copolymer comprising 30-60mol% styrene, 20-60mol% maleic monoester (e.g., monoethyl maleate), or 20mol% (meth)acrylate (e.g., methyl (meth)acrylate) and 0-20mol% maleic acid and having an acid value of 50-300 is neutralized to a degree of neutralization of the carboxyl groups of the copolymer of 7-100% to obtain a protective colloid comprising a water-soluble salt of the copolymer. 10-1,000pts.wt. ethylenically unsaturated monomer comprising 10-100wt% styrene, 0-50wt% nitrogen-containing ethylenically unsaturated monomer and 0-50wt% other ethylenically unsaturated monomer is emulsion-polymerized at 20-95 deg.C in the presence of 100pts.wt. (in terms of solid matter) above protective colloid.